



PRODUCT DATA SHEET

PRODUCT CODE: C252FR

SUPAGROUT FIBER REINFORCED

Description

SUPAGROUT FR is a non-shrink cementitious grout with fiber. The fiber are single filaments, measuring 32 microns in diameter, cut in lengths of 6-12mm. The fibre has been treated to improve initial dispersion and bonding capabilities of the grout

Principal uses

- Grouting of large compressors
- Pulp and paper dryers
- Rolling mills
- Applications involving impact and stress
- Baseplates and anchors

Advantages

- Controlled expansion
- Adjustable consistency
- High bond strength to steel and concrete
- High early strength development
- Medium flowability
- Hairline crack resistance
- Improved ductility properties

Performance data

Property	Typical results		
	24 hours	14 days	28 days
Compressive strength			
Water @ 4ℓ per 25kg	28Mpa	59Mpa	63Mpa
Water @ 4.85ℓ per 25kg	20Mpa	57Mpa	59Mpa

An unrestrained expansion of 1% to 4% is typical
Restrained expansion 0 - 0.4%

Workability

The product can be mixed either into a ram-able consistency or flowable depending on the requirements

Surface preparation

Concrete substrate must be structurally sound. Remove all oil, grease, paint, corrosion, dust and surface deposits. This can be done by wire brush or sand blasting. Ensure surface is wet or prime with Plaster Key to improve bond

Limitations

Do not grout at temperatures below 9°C. Avoid excessive heat 35°C and higher, wet hessian may be used to reduce evaporation rate. Grout cannot be reworked by later addition of water. Use curing compounds for improved results

Mixing instructions

Pre wet concrete mixer, add between 3.5ℓ and 4.5ℓ of water into the mixer, depending on the consistency required. Add the contents of the bag and mix until desired slump is achieved

Yield

Mixed with 3.5ℓ of water will yield 12ℓ
Mixed with 4.5ℓ of water will yield 14ℓ

Set time

Water content	Initial set	Final set
4ℓ per 25kg	2 hours	3 hours
4.5ℓ per 25kg	2hr35min	4 hours

Packaging

SUPAGROUT FR is available in 25kg bags

Safety & handling

Wear dust masks when mixing. Use gloves, eye protection at all times. Should the product come into contact with eyes, wash immediately and seek medical advice

Shelf Life & Storage

12 months when stored in a cool dry place, failure to comply with these recommendations will result in a reduction in shelf life

Notes

For any epoxy grouting, precision grouting, rapid set grouting consult your local representative for related products to suit specific requirements
For further instruction please consult your local representative for a method statement

Note: The information and specifications provided is to the best of our knowledge. The technical data contained herein are true and accurate at the date of issue and are subject to change without prior notice. No guarantee of accuracy is given or implied. We guarantee our products to conform to ASHAKepoxerite quality control. We cannot be held responsible or liable, directly or in directly for the use of our products, coverage, performance or injury resulting from use, as we have no control over the method of application used or site conditions. For further technical and method statements, contact our Technical representatives.