



**PRODUCT DATA SHEET**

**PRODUCT CODE: C257KT**

**SUPAGROUT KRYSTAL TECH**

**Description**

SUPAGROUT KT is a non-shrink cementitious grout containing Nano technology to form hydration crystals. These needle-like crystals block the capillary pores and micro-cracks within the mortar to dramatically reduce permeability and water absorption of grout

**Principal uses**

- Used to reduce permeability of grout
- Void filling in concrete
- Base plates, bearings, columns and crane rails

**Advantages**

- Improves resistance to cracking
- Improves adhesion
- Self-seals hairline cracks
- Reactivates in the presence of moisture even years later
- Good flow characteristics

**Performance data**

Property	Typical results		
Compressive strength	24 hours	14 days	28 days
Water @ 4ℓ per 25kg	28Mpa	59Mpa	63Mpa
Water @ 4.85ℓ per 25kg	20Mpa	57Mpa	59Mpa

An unrestrained expansion of 1% to 4% is typical  
Restrained expansion 0 - 0.4%

Flexural strength @28 days           8.2Mpa  
Tensile Strength @ 28 days           4.3Mpa

**Workability**

The product can be mixed either into a ram-able consistency or flowable depending on the requirements

**Surface preparation**

Concrete substrate must be structurally sound. Remove all oil, grease, paint, corrosion, dust and surface deposits. This can be done by wire brush or sand blasting. Saturate with clean water prior to applying the grout

**Limitations**

Do not grout at temperatures below 9°C. Avoid excessive heat 35°C and higher, wet hessian may be used to reduce evaporation rate. Grout cannot be reworked by later addition of water. Ensure Grout remains moist for at least 3-7 days to ensure crystal growth

**Mixing instructions**

SUPAGROUT KT will require less water than usual. Pre wet concrete mixer, add between 3ℓ and 4ℓ of water into the mixer, depending on the consistency required. Add the contents of the bag and mix until desired slump is achieved

**Curing**

Proper curing is essential to achieve the benefits and performance of the grout. Wet curing the grout with a fog mist spray, sprinkler or wet burlap for 3 to 7 days is recommended. Protect fresh applications from wind and direct sunlight

**Yield**

Mixed with 3.5ℓ of water will yield 12ℓ  
Mixed with 4.5ℓ of water will yield 14ℓ

**Set time**

Water content	Initial set	Final set
4ℓ per 25kg	2 hours	3 hours
4.5ℓ per 25kg	2hr35min	4 hours

**Packaging**

SUPAGROUT KT is available in 25kg bags

**Safety & handling**

Wear dust masks when mixing. Use gloves, eye protection at all times. Should the product come into contact with eyes, wash immediately and seek medical advice

**Shelf Life & Storage**

6 months when stored in a cool dry place, failure to comply with these recommendations will result in a reduction in shelf life

Note: The information and specifications provided is to the best of our knowledge. The technical data contained herein are true and accurate at the date of issue and are subject to change without prior notice. No guarantee of accuracy is given or implied. We guarantee our products to conform to ASHAKepoxerite quality control. We cannot be held responsible or liable, directly or in directly for the use of our products, coverage, performance or injury resulting from use, as we have no control over the method of application used or site conditions. For further technical and method statements, contact our Technical representatives.