



PRODUCT DATA SHEET

PRODUCT CODE: E280

POLYESTER ANCHOR GROUT

Description

E280 is a 2 component free flow polyester grout, specifically designed for ultrafast anchoring of various components

Principal uses

Polyester grouts are formulated to provide a high strength chemical resistant grouting medium for anchoring of starter bars, dowels, foundation bolts, ground anchors and base plates for building systems, as well as rail and crane tracks vertically down into substrates

Advantages

- Can be placed into wet or damp holes
- Ultrafast setting
- High early strength
- Corrosion resistant
- Easy to mix and apply
- Good chemical resistance

Performance data

Compressive strength	1day	105Mpa
Tensile strength	7day	13Mpa
Flexural strength	7day	34Mpa

Surface preparation

Remove all loose material, rust and any oil based residue where the product will be applied. This can be done by wire brushing, sanding, grinding or sand blasting the surface

Pot life & Curing

The product has a 15minute pot life at an ambient temperature of 25°C. Should the temperature increase, expect an accelerated reaction. In typical applications the product will be touch dry in 45 minutes and fully cured in 7 days

Application

Hole preparation- holes should be drilled using air or rotary percussive drilling equipment. If diamond core or non-percussive drills are used, the sides of the hole must be thoroughly roughened. Remove dust from holes compressed air

Mixing- pour the resin component into container supplied, while stirring, add the activated filler component. Once the filler component is completely added, mix further until smooth. A mechanical mixer such as a low speed drill or mixer paddle is recommended

Application- Once mixed, pour the grout into the drilled hole, taking care not to trap air or water. The fixing should be immediately pushed slowly down into the resin with a twisting action, displacing the resin up towards the top of the hole. The bolt must then be left undisturbed until the resin has set

Limitations

Do not use E280 below 5°C and above 30°C. Please note that temperatures exceeding 22° and high humidity would reduce pot life considerably

Safety & Handling

Epoxy resin components may cause skin irritation. The product is low in acute oral toxicity. At room temperature, there is exposure to vapours from the product that may cause allergic skin reaction in humans. Safe handling can best be accomplished by adhering to the following rules:

- Work in well ventilated areas
- Wear PVC gloves, safety glasses and aprons
- Use soap and water after using epoxies to remove any residue
- In the event of contact with eyes flush with copious amounts of water. Seek immediate medical attention
- Prior to mixing and curing the product is harm full to the environment

Packaging

The product is a 2 component kit.
The following kit sizes are available; 1ℓ and 5ℓ

Shelf life & storage instructions

12 months when stored in a cool dry place, failure to comply with these recommendations will result in a reduction in shelf life

Note: The information and specifications provided is to the best of our knowledge. The technical data contained herein are true and accurate at the date of issue and are subject to change without prior notice. No guarantee of accuracy is given or implied. We guarantee our products to conform to ASHAKepoxerite quality control. We cannot be held responsible or liable, directly or in directly for the use of our products, coverage, performance or injury resulting from use, as we have no control over the method of application used or site conditions. For further technical and method statements, contact our Technical representatives.