

SOUDAFLEX 40 FC**Revision:18/01/2011****Page 1 of 2****Technical Data:**

Base	Polyurethane
Consistency	Paste
Curing System	Moisture Cure
Skin formation (20°C/65% R.H.)	Ca. 15 min.
Curing Rate (20°C/65% R.H.)	3 mm/24h
Hardness (DIN 53505)	40 ± 5 Shore A
Specific Gravity (DIN 53479)	1,30 g/ml
Temperature Resistance	-30°C to +90°C
Elastical Recovery (ISO 7389)	> 80 %
Maximum allowed Distortion	20 %
Elasticity Modulus 100% (DIN 53504)	0,80 N/mm ²
Maximum Tension (DIN 53504)	1,70 N/mm ²
Elongation at Break (DIN 53504)	700 %

Product:

Soudaflex 40 FC is a high quality, one component polyurethane sealant with high modulus for a wide range of sealing and bonding applications

Characteristics:

- Very easy application
- Stays elastic after curing
- Very good adhesion on many materials
- Excellent resistance to many chemicals
- Excellent resistance to UV radiation
- Especially developed for concrete applications

Applications:

- All sealing and bonding applications in the building industry
- Structural bonding in vibrating constructions

Packaging:

Colour: white, grey, black, other colours on request
Packaging: alu cartridge 310 ml, sausages 600 ml

Shelflife:

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°

Surfaces:

Type: all usual building surfaces, most metals, polyesters and many plastics – not on glass.
State of Surface: clean, dry, free of dust and grease
Preparation:

- In very warm and moist climates we recommend the use of Primer 100 for applications on porous surfaces,
- No primer required for non porous surfaces.
- Non porous surfaces may be activated by Surface Activator

We recommend a preliminary compatibility test.

Joint Size:

Minimum Width: 2mm (in bonding applications)
5mm (in joints)

Maximum Width: 10mm (in bonding applications)
30mm (in joints)

Minimum Depth: 5mm (in joints)

Recommendation:

- Joints of 12mm or less : depth = width
- Joints of more than 12mm : 2 x depth = width

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

SOUDAFLEX 40 FC

Revision:18/01/2011**Page 2 of 2****Application:***Method:* caulking gun*Application temperature:* +5°C to +35°C*Clean:* with white spirit immediately after use*Finishing:* with a soapy solution before skinning*Repair:* with same product**Health- and Safety Recommendation:**

Apply the usual industrial hygiene.

Remarks:

- In order to ensure the correct performance of our product, Soudal recommends a small adhesion test.
- When painted with oxidative drying paints disturbances in the drying of the paints may occur

Tests and certificates:

ISO 11600 F 20 HM

AENOR Certificate N°047/000278

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.